



# **IS-2006**

# (MIL-PRF-16173E GRADE 1 & 2)

Corrosion Preventive Compound transparent non-tacky film

Protects Metals Against Rust and Corrosion for Indoor & Outdoor Storage

## **Description:**

**IS-2006** is a corrosion preventive compound specially designed to protect metals against rust and corrosion for indoor and outdoor storage, and shipment. When used as recommended **IS-2006** is easy and economical to apply and remove and provides a durable, long lasting, transparent, nontacky film suitable for protecting metal surfaces against the elements of corrosive environment.

### **Specifications:**

Meets requirements of U.S. Military Specification MIL-PRF-16173E GRADE 1 & 2 transparent, non-tacky film.

## <u>Properties – Typical Values:</u>

- Solvent based, free of benzene, trichloroethylene and perchloroethylene.
- Solvent distillation end point (max): 210°C.
- Flash point: >38°C.
- Drying to touch time: Not more than 3 hours.
- Salt spray exposure time (min): 14 days.

This type of transparent, non-tacky film gives better results against corrosion in relation with other products, which form a soft film.

#### **Intended Usage:**

- a) For general purpose indoor and limited outdoor preservation of corrodible metals with or without an overwrap and where handling, stacking and counting requires a tack-free coating.
- b) For storage protection of precision parts, machine tools, pistons, valves and where a transparent coating is required in addition to properties indicated in item (a) above.
- c) For protection of machinery and parts designed for export and where salt spray contamination is likely to occur.
- d) Where there is no requirement for miscibility with lubricating oil and where ease of removal with stoddard's solvent (P-D-680) is important.

### **Directions for Use:**

**IS-2006** is used in full strength by spray, immersion or swab. Allow **IS-2006** to dry to form a transparent, non-tacky, protective anti-corrosive film.

#### **Product Removal:**

**IS-2006** is removed from parts by solvent wiping, steam gun cleaning or alkaline hot tank immersion.

E-mail: eur98@otenet.gr - http://www.eurochem.gr, www.eurochemsa.com



## **Caution:**

Avoid contact with skin and eyes. For further information refer to Material Safety Data Sheet (MSDS).

# **Packaging:**

**IS-2006** is offered in 400 ml aerosol spray and 4, 13, 20, 30 liter pails or 210 liter drums.

E-mail: eur98@otenet.gr - http://www.eurochem.gr, www.eurochemsa.com